

## TECHNICAL INFORMATION

<b>PRODUCT</b>	<b>KLX</b>
<b>DESCRIPTION</b>	Metallized film-foil Polyester film mylar (polyethylene terephthalate) 12 µ Polyester film with metallized lacquer coating (Al)
<b>FIELD OF USE</b>	Transfer film for finishing of textiles, leather and leatherette
<b>GUIDELINES FOR APPLICATION</b>	It's recommended to apply an adhesive substrate on the material to be rolled. After putting the foil KLX in contact with the support, making sure that no wrinkles are formed, we proceed with the application on rotary press or flat press.  Printing temperature: 100-120°C  Pressure: low/medium  Time: 2-6 second  Cool and remove the mylar film after about 12 hours  These conditions represent an indication of use and depict the parameters tested in our company. These parameters may change depending on the characteristics of your transfer machine and the support material
<b>CHARACTERISTIC</b>	Foil are particularly suitable for the finishing of leather for garment industry, upholstery, footwear and leather goods in general. There are a wide range of colours to meet the requirements of the customer
<b>INFORMATION</b>	Length of rolls: 61, 122, 244, 500, 1000 m Height: 150 cm Packaging: cylindrical fibreboard roll or fibreboard box.  <u>Storage</u> : stored for a maximum of 12 months at temperature between 5°C and 35°C, protect from moisture and direct sunlight .

This release is simply not binding for future reference, we can not therefore offer any sort of warranty and assume no responsibility for the successful application using this information.  
Please adapt all data on our products to existing conditions and the support material used

Update: 17/07/2017