

TECHNICAL INFORMATION

PRODUCT	LACCA LMF TC (series)
DESCRIPTION	Polyester film mylar (polyethylene terephthalate) Printing inks based on nitroacrylic and nitropolyuretanic resin
FIELD OF USE	Transfer film for finishing of textiles, leather and leatherette
GUIDELINES FOR APPLICATION	<p>It's recommended to apply an adhesive substrate. After putting the film in contact with the support with thermoadhesive resin, making sure that no wrinkles are formed, we proceed with the application on rotary press or flat press</p> <p>Printing temperature: 130-150°C</p> <p>Pressure: medium</p> <p>Time: 2-6 second</p> <p>Cool and remove the mylar film after about 12 hours</p> <p>These conditions represent an indication of use and depict the parameters tested in our company. These parameters may change depending on the characteristics of your transfer machine and the support material</p>
CHARACTERISTIC	Films are particularly suitable for the finishing of leather for garment industry, upholstery, footwear and leather goods in general. There are a wide range of colours in matt and shining version.
INFORMATION	<p>Length of rolls: 500 m Height: 160 cm Packaging: cylindrical fibreboard roll or fibreboard box.</p> <p><u>Storage</u>: stored for a maximum of 12 months at temperature between 5°C and 35°C, protect from moisture and direct sunlight .</p>

This release is simply not binding for future reference, we can not therefore offer any sort of warranty and assume no responsibility for the successful application using this information.
Please adapt all data on our products to existing conditions and the support material used

Update: 01/08/2016