

TECHNICAL INFORMATION

PRODUCT

LAX T LUCIDO

DESCRIPTION

Polyester film (polyethylene terephthalate) 12 μ
Thermoplastic film of resin, transparent

FIELD OF USE

Film for finishing of textiles, leather and leatherette

GUIDELINES FOR APPLICATION

It's recommended to apply an adhesive substrate. After putting the film in contact with the support, making sure that no wrinkles are formed, we proceed with the application on rotary press or flat press.

Printing temperature: 110-120°C

Pressure: suitable to support material

Time: 2-6 second

Cool and remove the mylar film after about 12 hours

These conditions represent an indication of use and depict the parameters tested in our company. These parameters may change depending on the characteristics of your transfer machine and the support material

CHARACTERISTIC

Film is particularly suitable for the glossy finishing of leather for garment industry, upholstery, footwear and leather goods in general.

INFORMATION

Length of rolls: 1000 m
Height: 150/180 cm
Packaging: roll.

Storage: stored for a maximum of 12 months at temperature between 5°C and 35°C, protect from moisture and direct sunlight .

This release is simply not binding for future reference, we can not therefore offer any sort of warranty and assume no responsibility for the successful application using this information.
Please adapt all data on our products to existing conditions and the support material used

Update: 09/04/2018