

TECHNICAL INFORMATION

PRODUCT

NAPPALAN (series)

DESCRIPTION

Polyester film mylar (polyethylene terephthalate) 19 µ
Thermoplastic film of polyurethane resin transparent or coloured

FIELD OF USE

Transfer film for finishing of textiles, leather and leatherette

GUIDELINES FOR APPLICATION

NAPPALAN is a thermoplastic film then does not require any adhesive substrate. After putting the film in contact with the support, making sure that no wrinkles are formed, we proceed with the application on rotary press or flat press

Printing temperature: 100-120°C

Pressure: low/medium

Time: 2-6 second

Cool and remove the mylar film after about 8/12 hours

These conditions represent an indication of use and depict the parameters tested in our company. These parameters may change depending on the characteristics of your transfer machine and the support material

CHARACTERISTIC

Films are particularly suitable for the finishing of leather for garment industry, upholstery, footwear and leather goods in general. There are a wide range of colours in matt and shining version.

INFORMATION

Length of rolls: 200, 500 m
Height: 150 cm, 180 cm (on request)
Packaging: cylindrical fibreboard roll or fibreboard box.

Storage: stored for a maximum of 12 months at temperature between 5°C and 35°C, protect from moisture and direct sunlight .

This release is simply not binding for future reference, we can not therefore offer any sort of warranty and assume no responsibility for the successful application using this information.
Please adapt all data on our products to existing conditions and the support material used

Update: 17/05/2016