

## TECHNICAL INFORMATION

### PRODUCT

## T-LAST (series)

### DESCRIPTION

Metallized film-foil elastic self-adhesive  
Polyester film mylar (polyethylene terephthalate) 12  $\mu$   
Polyester film with metallized lacquer coating (Al)  
Self adhesive film of polyurethane resin

### FIELD OF USE

Transfer film for finishing of textiles, leather and leatherette

### GUIDELINES FOR APPLICATION

Foil is a self adhesive film but, in some cases, it's recommended to apply a further adhesive substrate on the material to be rolled.

After putting the foil T-LAST in contact with the support, making sure that no wrinkles are formed, we proceed with the application on rotary press or flat press

Printing temperature: 100-120°C

Pressure: appropriate to the material to be rolled

Time: 2-6 second

Cool and remove the mylar film after about 12 hours

These conditions represent an indication of use and depict the parameters tested in our company. These parameters may change depending on the characteristics of your transfer machine and the support material

### CHARACTERISTIC

Foil are particularly suitable for the finishing of leather for garment industry, upholstery, footwear and leather goods in general.  
There are a wide range of colours to meet the requirements of the customer

### INFORMATION

Length of rolls: 200 m  
Height: 150 cm  
Packaging: cylindrical fibreboard roll or fibreboard box.

Storage: stored for a maximum of 12 months at temperature between 5°C and 35°C, protect from moisture and direct sunlight .

This release is simply not binding for future reference, we can not therefore offer any sort of warranty and assume no responsibility for the successful application using this information.  
Please adapt all data on our products to existing conditions and the support material used

Update: 17/07/2017